



Main Branch:

PO Box 23781
New Orleans, La 70183
www.rblc.com

Phone: 504-841-0035

Fax: 504-841-0036

E-mail: sales@rblc.com

San Diego Branch:

1995 Main Street
San Diego, Ca 92113

Phone: 619-234-2620

Fax: 619-234-2432

All statements herein are expressions of opinion that we believe to be true and reliable. However, they are represented without guaranty or warranty. Statements regarding the use of our products for their use alone or in conjunction with any other materials should not be intended as recommendations. Nothing herein is intended to infringe on any patents. No patent warranty of any kind, express or implied is hereby made.

IMO / US Navy Certified Insulations

RB, L.L.C.

Insulation with integrity, from people who care.

Nautica IMO CF Mineral Wool Board

Description:

Nautica Mineral Wool Insulation with IMO CF combines fire performance with efficient thermal and acoustic properties. It has a tough, paintable, white fiberglass facing. It is generally used on bulkheads, decks and stiffeners.

It is approved by the U.S. Coast Guard (USCG 164.109 and 164.112) for thermal applications on ships. It is rated by the USCG/IMO as "structural insulation" and upgrade an "Class A" steel division to A-60 (USCG 164.107).

Installation is with insulation pins and clips, and joints can be covered with fiberglass lagging tape.

Specifications: U.S. Coast Guard: 164.109/164.107/164.112

Standard Sizes:
1" x 24" x 48" — for A-60 deck stiffeners
1-1/2" x 24" x 48" — for A-60 bulkhead stiffeners
2" x 24" x 48" — for A-60 deck
3" x 24" x 48" — for A-60 bulkhead

Base Board: 7 pcf Mineral Wool Board
Passes IMO FTP A.754, USCG 164.109-107

Facing: Glass cloth, 12.8 oz/square yard
Color: White
MIL-C-20079 Type I, Cl. 2

Flame Spread/

Smoke: Meets Part 2 and 5 of the FTP Code

Thermal Conductivity: .24@75°F Temp (BTU-IN/SF/°F/HR)