



IMO / US Navy Certified Insulations

RB, L.L.C.

Insulation with integrity, from people who care.

Main Branch:

PO Box 23781
New Orleans, La 70183
www.rblc.com

Phone: 504-841-0035
Fax: 504-841-0036
E-mail: sales@rblc.com

San Diego Branch:

1995 Main Street
San Diego, Ca 92113

Phone: 619-234-2620
Fax: 619-234-2432

All statements herein are expressions of opinion that we believe to be true and reliable. However, they are represented without guaranty or warranty. Statements regarding the use of our products for their use alone or in conjunction with any other materials should not be intended as recommendations. Nothing herein is intended to infringe on any patents. No patent warranty of any kind, express or implied is hereby made.

Nautica IMO LF Acoustic Board with Lead Face

Description:

Nautica IMO LF is an excellent high transmission loss component of acoustic treatments. The fiberglass acoustic hullboard provides a non-combustible decoupling layer, while the 1.5 pound per square foot lead facing blocks unwanted noise. Both the fiberglass board and the IMO LF meet USCG and IMO's stringent fire requirements.

This is the only USCG approved high transmission loss system that is conveniently installed as a single component.

Installation is with insulation pins and clips.

Specifications:	U.S. Coast Guard: Board: 164.109 Facing: 164.112/0099/0
Standard Sizes:	1" x 24" x 48" (96 sf/ctn) 2" X 24" 48" (48 sf/ctn)

Base Board:	Nominal 3 pcf Fiberglass Board
Lead Insert:	1.5 pound per square foot lead
Flame Spread/ Smoke:	Meets Part 2 and 5 of the IMO FTP Code
Thermal Conductivity:	.23@75°F Temp (BTU-IN/SF/°F/HR)

Est. Sound Transmission Class: 2" = 28
Sound Transmission Loss (db)

Freq	125	250	500	1000	2000	4000	STC
2" Thk	14	14	24	37	49	57	28