



IMO / US Navy Certified Insulations

RB, L.L.C.

Insulation with integrity, from people who care.

Main Branch:

PO Box 23781
New Orleans, La 70183
www.rblc.com

Phone: 504-841-0035
Fax: 504-841-0036
E-mail: sales@rblc.com

San Diego Branch:

1995 Main Street
San Diego, Ca 92113

Phone: 619-234-2620
Fax: 619-234-2432

Nautica TA-301 RMW Acoustic Hullboard

Description:

Inherently fire resistant, this light weight hullboard was developed for significant weight reduction of thermal insulation for the U.S. Navy. The polyimide foam board, Solimide TA-301 is approximately 1/6th the weight of traditional fiberglass hullboard. The RMW facing provides a tough moisture and oil resistant acoustic interior finish. Few if any stud fasteners are required.

Specifications:	U.S. Navy: base material DOD-I-24688 Type I
Facing:	Reinforced polyester film IAW Mil-I-22023 Ty III
Standard Sizes:	1 x 24 x 48 (160 sf/carton) 2 x 24 x 48 (80 sf/carton)
Weight:	1" .10 lbs/sf 2" .14 lbs/sf

Base Board: Solimide TA-301 Polyimide foam per DOD-I-24688, 0.4 pcf density

Facing: Polyester Film with 10x10 Glass Fiber Mesh

Color: White

Weight: 2.8 Oz/Square Yard

Permeability: 0.5 Perms (MVTR-ASTM-3-96-66A)

Tear Strngth: Warp/Fill—7 Lb Min. (ASTM-D-1117)

Flame Spread/

Smoke: Meets Part 2 of the FTP Code

Thermal Conductivity: .30@75°F Temp (BTU-IN/SF/°F/HR)

Noise Reduction

Coefficient: Standard 2" TA-301 RMW NRC=55

All statements herein are expressions of opinion that we believe to be true and reliable. However, they are represented without guaranty or warranty. Statements regarding the use of our products for their use alone or in conjunction with any other materials should not be intended as recommendations. Nothing herein is intended to infringe on any patents. No patent warranty of any kind, express or implied is hereby made.